FILTRALITE®



Filtralite[®] Pure NC 0,8-1,6



PRODUCT DESCRIPTION

Filtralite® Pure NC 0,8-1,6 is high quality filter media, manufactured from expanded clay material, used for filtration in drinking water treatment and pre-treatment for desalination.

ADVANTAGES

Filtralite® media, with its highly porous structure, enables improved filter efficiency by longer filter runs between backwashes, which means reduced energy and water consumption and higher water production, consequently giving reduced operating costs.

EXPLANATIONS

N = Normal density, M = Medium density, H = High density, C = Crushed, R = Round

PRODUCT SPECIFICATION

Commercial name	FILTRALITE® NC 0,8-1,6		
Density	Bulk density, compressed: 515 kg/m3 Particle density: 1250 kg/m3		
Type of material	Expanded clay		
Appearance	Crushed particles, porous surface structure		
Manufactured by	Leca Rælingen (Saint-Gobain Group), Norway		
Version	8		

Size and weight	Value	Deviation	Comments
Particle size range	0,8-1,6 mm	< 0,8 mm max. 5 % > 1,6 mm max. 5 %	EN 12905
Bulk density, dry, compressed	515 kg/m ³	± 75 kg/m ³	EN 1097-3, 10 strokes
Particle density, apparent	1250 kg/m ³	± 150 kg/m ³	EN 1097-6, Annex E

Other properties	Value	Comments	
Voids	~61 %	EN 1097-3, approximate value	
Acid solubility	< 7 %	EN 12902	

A Saint-Gobain brand

Leca Norge AS - Reg. of ent. NO 918 799141 MVA/VAT Årnesvegen 1 • N-2009 Nordby • Norway

Telephone: +47 41 43 71 00

Chemical composition, approximate values							
SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	K ₂ O	CaO	Na₂O		
63 %	17 %	7 %	4 %	2 %	2 %		

DISCLAIMER

The information provided in this data sheet is based on our current knowledge and experience. All the above information must be considered as guidelines. It is the user's responsibility to ensure that the product is suitable for the intended use and perform self-monitoring. The user is responsible if the product is used for purposes other than those recommended, or improper execution. We are available for consultation in the use of our products.